

FLEXIBLE POLYOLEFIN

2 : 1 Shrink Ratio

PBDE - Free

UL/CSA RECOGNIZED 125° C and 600V (VW-1)



RoHS Compliant

TYPICAL FEATURES	
<p>1) Sumitube F2(Z) is a very flexible, low recovery temperature, flame-retarded, heat-shrinkable polyolefin tubing that is recognized by Underwriters' Laboratories (UL) under Subject 224 as UL VW-1, and the Canadian Standards Association (CSA) at 125° C. Sumitube F2(Z) is PBDE & PBB-free.</p> <p>2) Low recovery temperature benefits the user in more rapid installation, with less potential damage to heat sensitive component insulation systems.</p>	<p>3) Shrink temperature is 90° C.</p> <p>4) Operating temperature range is -55° C to +125° C.</p> <p>5) Sumitube F2(Z) is recommended for all general purpose applications such as insulating, color coding, bundling and light harness jacketing where UL or CSA recognition as VW-1 rated material is desirable.</p> <p>6) Sumitube F2(Z) is a direct replacement for Sumitube F2.</p>

STANDARD SIZES

SIZE	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
3/64	.046	1.2	.023	0.6	.016	0.40
1/16	.063	1.6	.031	0.8	.017	0.43
3/32	.093	2.4	.046	1.2	.020	0.51
1/8	.125	3.2	.062	1.6	.020	0.51
3/16	.187	4.8	.093	2.4	.020	0.51
1/4	.250	6.4	.125	3.2	.025	0.64
3/8	.375	9.5	.187	4.8	.025	0.64
1/2	.500	12.7	.250	6.4	.025	0.64
3/4	.750	19.1	.375	9.5	.030	0.76
1	1.000	25.4	.500	12.7	.035	0.89
1 1/2	1.500	38.1	.750	19.1	.040	1.02
2	2.000	50.8	1.000	25.4	.045	1.14
3	3.000	76.2	1.500	38.1	.050	1.27
4	4.000	101.6	2.000	50.8	.055	1.40

Standard Colors: Black, White, Red, Yellow (Other colors subject to factory acceptance and quote)
Standard Package: Spooled (S) or 4 foot lengths (4'). Note: Metric sizes also available per factory quote.
How to Order: (Type of material) (Size) (Color) (Packaging)
Example: F2(Z) 1/4 Black S

F2(Z) Specification Values

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Low temperature flex (-55°C) Heat resistance (158°C, 168 Hrs.) Elongation (%) Secant modulus (psi) Deformation (125°C, 1 Hr.) (%) Longitudinal change (%)	UL 224 UL 224 ASTM D792 AMS-DTL-23053 UL 224 ASTM D882 UL 224 AMS-DTL-23053	1500 MIN. 200 MIN. 1.35 MAX. No cracking 100 MIN. 25000 MIN. 50 MAX. ±5
Electrical: Dielectric withstand (volts) Volume resistivity (ohm-cm)	UL 224 UL 224	2500 MIN. 1.0 X 10 [#] MIN.
Chemical: Corrosion Copper stability (158°C 168 Hrs.) Elongation (%) Water absorption (%) Flammability Shrink temperature, nominal	UL 224 UL 224 ASTM D570 UL 224 VW-1 ---	No corrosion 100 MIN. 0.5 MAX. pass 90°C

Specification reference: UL 224 125°C, 600V, VW-1
 File E48762 YDPU2
 CSA-C22.2 No. 198-M1986 125°C, 600V
 File LR33298

Marking: SUMITUBE F2(Z) is surface printed with recognized UL / CSA markings.

 **SUMITOMO ELECTRIC**
INTERCONNECT PRODUCTS INC
www.cambridge-technologies.com

Rev. 7/6/05

